



UBIQ Technology Co., Ltd.

6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

Tel : +886-3-3312677 e-mail: sales@ubiq.com.tw

Fax : +886-3-3357412 Website: www.ubiq.com.tw

# KS-4導電性カーボンブラック

モデル番号 : KS-4

商品詳細:

\*ご興味を持たれた商品のお問い合わせ・

お見積もりはUBIQへお願い致します。



ITEMS	TEST RESULTS
PURITY	
Ash(810 °C) %	0.01
Moisture %	<0.3
Trace Elements(OES)	
Al ppm	<1.5
Ca ppm	9
Cu ppm	<1
Cr ppm	1.0
Co ppm	1
Ni ppm	1
Mo ppm	<0.5
Si ppm	19
Sb ppm	<2
As ppm	<0.5
Pb ppm	<0.8
Ti ppm	2
Fe ppm	18
V ppm	4
DENSITY	
Xylene g/cm <sup>3</sup>	2.246
Scott (not bagged) g/cm <sup>3</sup>	0.075
SURFACE AREA BET m <sup>2</sup> /g	25.3
PARTICLE SIZE Laser Diffraction	
d 10 um	1.0
d 50 um	2.1
d 90 um	3.9