

# KS-6導電性カーボンブラック

モデル番号 : KS-6

商品詳細:

\*ご興味を持たれた商品のお問い合わせ・

お見積もりはUBIQへお願い致します。



| ITEMS                              | TEST RESULTS |
|------------------------------------|--------------|
| PURITY                             |              |
| Ash(810 °C) %                      | 0.06         |
| Moisture %                         | 0.1          |
| Trace Elements(OES)                |              |
| Al ppm                             | 10           |
| As ppm                             | <0.5         |
| Ca ppm                             | 90           |
| Co ppm                             | <1           |
| Cr ppm                             | <1           |
| Cu ppm                             | <1           |
| Fe ppm                             | 75           |
| Mo ppm                             | <1           |
| Ni ppm                             | 2            |
| Pb ppm                             | <2           |
| Sb ppm                             | <0.1         |
| Si ppm                             | 90           |
| Ti ppm                             | 7            |
| V ppm                              | 3            |
| S ppm                              | 50           |
| DENSITY                            |              |
| Scott g/cm <sup>3</sup>            | 0.07         |
| Xylene g/cm <sup>3</sup>           | 2.255        |
| SURFACE AREA BET m <sup>2</sup> /g | 20           |
| PARTICLE SIZE Laser Diffraction    |              |
| d 10 um                            | 1.6          |
| d 50 um                            | 3.4          |
| d 90 um                            | 6.5          |