



UBIQ Technology Co., Ltd.

6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

Tel : +886-3-3312677 e-mail: sales@ubiq.com.tw

Fax : +886-3-3357412 Website: www.ubiq.com.tw

## Super P導電性カーボンブラック

モデル番号 : Super-P

商品詳細:



ITEMS	TEST RESULTS
Density (in the bag) kg/m <sup>3</sup>	160
Carbon content %	>99.5
Absorption stiffness value ml/5g	32
Hydrochloric acid abs. value ml/5g	20.2
BET surface area m <sup>2</sup> /g	62
Ash content %	0.01
Moisture (as packed) %	0.1
Volatile matter (105-950°C) %	0.1
Toluene extract %	<0.1
Total Sulphur %	0.008
Total Iron (Fe) ppm	1.8
pH	9.4
Grit content(>20 microns) ppm	11
Specific resistance 50 kg/cm <sup>2</sup> ohm.cm	0.16
100 kg/cm <sup>2</sup> ohm.cm	0.11