

CMC リチウムイオン電池負極用

モデル番号 : WALCRT 30000PA

商品詳細:



Test items	Standard value	Actual value
Exterior	White or light yellow fibrous powder	White or light yellow fibrous powder
Viscosity mpa.s 2% water	2500-2800	2650
D.S	0.65-0.75	0.70
Chloride (NaCl)%	≤0.5	0.29
Moisture %	≤6.0	5.24
PH Value	6.5-8.5	6.8
Purity %	≥99	99.1
Fineness	95% pass 120 mesh	95% pass 120 mesh