



優必克科技股份有限公司
UBIQ Technology Co., Ltd.

330 桃園市桃園區大業路一段 18 號 6 樓之 1
6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)
電話 Tel : 03-331-2677 e-mail: sales@ubiq.com.tw
傳真 Fax : 03-335-7412 Website: www.ubiq.com.tw

助 導 劑

產品名稱 :助導劑

型號 :

■ KS-4



Analysis:

ITEMS	TEST RESULTS
PURITY	
Ash(810 °C) %	0.01
Moisture %	<0.3
Trace Elements(OES)	
Al ppm	<1.5
Ca ppm	9
Cu ppm	<1
Cr ppm	1.0
Co ppm	1
Ni ppm	1
Mo ppm	<0.5
Si ppm	19
Sb ppm	<2
As ppm	<0.5
Pb ppm	<0.8
Ti ppm	2

	Fe ppm	18
	V ppm	4
DENSITY		
	Xylene g/cm ³	2.246
	Scott (not bagged) g/cm ³	0.075
SURFACE AREA	BET m ² /g	25.3
PARTICLE SIZE	Laser Diffraction	
	d 10 um	1.0
	d 50 um	2.1
	d 90 um	3.9

*規格請向本公司洽詢



優必克科技股份有限公司
UBIQ Technology Co., Ltd.

330 桃園市桃園區大業路一段 18 號 6 樓之 1
6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)
電話 Tel : 03-331-2677 e-mail: sales@ubiq.com.tw
傳真 Fax : 03-335-7412 Website: www.ubiq.com.tw

Conductive Carbon Black /Graphite

Product name : Comductive Carbon Black /Graphite

Model:

- KS-4



Analysis:

ITEMS	TEST RESULTS
PURITY	
Ash(810 °C) %	0.01
Moisture %	<0.3
Trace Elements(OES)	
Al ppm	<1.5
Ca ppm	9
Cu ppm	<1
Cr ppm	1.0
Co ppm	1
Ni ppm	1
Mo ppm	<0.5
Si ppm	19
Sb ppm	<2
As ppm	<0.5
Pb ppm	<0.8
Ti ppm	2
Fe ppm	18
V ppm	4

DENSITY	Xylene g/cm ³	2.246
	Scott (not bagged) g/cm ³	0.075
SURFACE AREA	BET m ² /g	25.3
PARTICLE SIZE	Laser Diffraction	
	d 10 um	1.0
	d 50 um	2.1
	d 90 um	3.9

***If you are interested in any of our products,
or wish to place a customized order,
please contact us.**