



優必克科技股份有限公司
UBIQ Technology Co., Ltd.

330 桃園市桃園區大業路一段 18 號 6 樓之 1
6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)
電話 Tel : 03-331-2677 e-mail: sales@ubiq.com.tw
傳真 Fax : 03-335-7412 Website: www.ubiq.com.tw

助 導 劑

產品名稱 :助導劑

型號:

■ KS-6



Analysis:

ITEMS	TEST RESULTS
PURITY	
Ash(810 °C) %	0.06
Moisture %	0.1
Trace Elements(OES)	
Al ppm	10
As ppm	<0.5
Ca ppm	90
Co ppm	<1
Cr ppm	<1
Cu ppm	<1
Fe ppm	75
Mo ppm	<1
Ni ppm	2
Pb ppm	<2
Sb ppm	<0.1
Si ppm	90
Ti ppm	7

	V ppm	3
	S ppm	50
DENSITY	Scott g/cm ³	0.07
	Xylene g/cm ³	2.255
SURFACE AREA	BET m ² /g	20
PARTICLE SIZE	Laser Diffraction	
	d 10 um	1.6
	d 50 um	3.4
	d 90 um	6.5

*規格請向本公司洽詢



優必克科技股份有限公司

UBIQ Technology Co., Ltd.

330 桃園市桃園區大業路一段 18 號 6 樓之 1

6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

電話 Tel : 03-331-2677 e-mail: sales@ubiq.com.tw

傳真 Fax : 03-335-7412 Website: www.ubiq.com.tw

Conductive Carbon Black /Graphite

Product name : Comductive Carbon Black /Graphite

Model:

- KS-6



Analysis:

ITEMS	TEST RESULTS
PURITY	
Ash(810 °C) %	0.06
Moisture %	0.1
Trace Elements(OES)	
Al ppm	10
As ppm	<0.5
Ca ppm	90
Co ppm	<1
Cr ppm	<1
Cu ppm	<1
Fe ppm	75
Mo ppm	<1
Ni ppm	2

	Pb ppm	<2
	Sb ppm	<0.1
	Si ppm	90
	Ti ppm	7
	V ppm	3
	S ppm	50
DENSITY	Scott g/cm ³	0.07
	Xylene g/cm ³	2.255
SURFACE AREA	BET m ² /g	20
PARTICLE SIZE	Laser Diffraction	
	d 10 um	1.6
	d 50 um	3.4
	d 90 um	6.5

***If you are interested in any of our products,
or wish to place a customized order,
please contact us.**