



優必克科技股份有限公司  
UBIQ Technology Co., Ltd.

330 桃園市桃園區大業路一段 18 號 6 樓之 1  
6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)  
電話 Tel : 03-331-2677 e-mail: sales@ubiq.com.tw  
傳真 Fax : 03-335-7412 Website: www.ubiq.com.tw

## 助 導 劑

產品名稱： SUPER-P 助導劑

型號： Super-P



### Analysis:

ITEMS	TEST RESULTS
Density (in the bag) kg/m <sup>3</sup>	160
Carbon content %	>99.5
Absorption stiffness value ml/5g	32
Hydrochloric acid abs. value ml/5g	20.2
BET surface area m <sup>2</sup> /g	62
Ash content %	0.01
Moisture (as packed) %	0.1
Volatile matter (105-950°C) %	0.1
Toluene extract %	<0.1
Total Sulphur %	0.008
Total Iron (Fe) ppm	1.8
pH	9.4
Grit content(>20 microns) ppm	11
Specific resistance 50 kg/cm <sup>2</sup> ohm.cm	0.16
100 kg/cm <sup>2</sup> ohm.cm	0.11

\*規格請向本公司洽詢



優必克科技股份有限公司

UBIQ Technology Co., Ltd.

330 桃園市桃園區大業路一段 18 號 6 樓之 1

6F.-1, No.18, Sec. 1, Daye Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

電話 Tel : 03-331-2677 e-mail: sales@ubiq.com.tw

傳真 Fax : 03-335-7412 Website: www.ubiq.com.tw

# Conductive Carbon Black /Graphite

**Product name : Comductive Carbon Black**

**/Graphite**

**Model: Super-P**



**Analysis:**

ITEMS	TEST RESULTS
Density (in the bag) kg/m <sup>3</sup>	160
Carbon content %	>99.5
Absorption stiffness value ml/5g	32
Hydrochloric acid abs. value ml/5g	20.2
BET surface area m <sup>2</sup> /g	62
Ash content %	0.01
Moisture (as packed) %	0.1
Volatile matter (105-950°C) %	0.1
Toluene extract %	<0.1
Total Sulphur %	0.008
Total Iron (Fe) ppm	1.8
pH	9.4
Grit content(>20 microns) ppm	11
Specific resistance 50 kg/cm <sup>2</sup> ohm.cm	0.16
100 kg/cm <sup>2</sup> ohm.cm	0.11

**\*If you are interested in any of our products,  
or wish to place a customized order,  
please contact us.**